

**From Antiferromagnetic Order to Static Magnetic Stripes:  
The Phase Diagram of  $(\text{La,Eu})_{2-x}\text{Sr}_x\text{CuO}_4$ :**\*

H.-H. Klauss<sup>1</sup>, W. Wagener<sup>1</sup>, W. Kopmann<sup>1</sup>, D. Baabe<sup>1</sup>, D. Mienert<sup>1</sup>, F.J. Litterst<sup>1</sup>, M. Hücker<sup>2</sup>, B. Büchner<sup>1,2</sup>

<sup>1</sup> *Institut f. Metallphysik, TU Braunschweig, D-38106 Braunschweig, Germany*

<sup>2</sup> *II. Physikalisches Institut, RWTH Aachen, D-52056 Aachen, Germany*

The magnetic order of  $\text{La}_{1.8-x}\text{Eu}_{0.2}\text{Sr}_x\text{CuO}_4$  ( $x \leq 0.2$ ) has been investigated with  $\mu\text{SR}$  techniques. In this system a low temperature tetragonal (LTT) structure is present in the entire range of doping and it is possible to follow the evolution from the long range antiferromagnetic state at  $x = 0$  to the static magnetic stripes. We find a non-monotonic change of the Néel temperature with increasing  $x$  and the obtained magnetic phase diagram of the LTT phase resembles the generic phase diagram of the cuprates where the superconductivity is replaced by a second antiferromagnetic phase <sup>†</sup>. At a charge doping of  $x = 0.2$  a crossover from magnetic order to superconductivity has been found. New experiments show that the ground state at  $x = 0.2$  can be tuned from magnetism to superconductivity by a variation of the Eu content between 0.23 and 0.10 changing only the LTT lattice distortion.

---

\*This work was supported by the BMBF and the DFG

<sup>†</sup>Phys. Rev. Lett. **85** (2000) 4590